



ExxonMobil

High Density Polyethylene

ExxonMobil
Chemical

HD-7845 MMW-HDPE Blown Film Resin

Description

HD-7845 can be processed on high stalk, pocket extrusion or cast lines. Films made from the HD-7845 exhibit an excellent stiffness balance. High thermal stability provides excellent film appearance and high quality recycle. HD-7845 is particularly recommended as a blend component with LLDPE for stiff clear films.

Applications

- Oriented film products
- Protective packaging
- Deli wrap
- Specialty packaging

RECEIVED
JUN 17 2003
TC 1700

Resin Properties	Test Based On	Units (SI)	Typical Value ²
Melt Index (I ₂)	ExxonMobil Method	g/10 min	0.45
HLMI (I ₂₁)	ExxonMobil Method	g/10 min	30
Density	ExxonMobil Method	g/cm ³	0.958

Film Properties¹ (1.0 mil)

Tensile Strength	@ Yield	MD	ASTM D-882	psi (MPa)	4700 (32)
		TD			3750 (26)
	@ Break	MD			10,500 (72)
		TD			5300 (36)
Ultimate Elongation		MD	ASTM D-882	%	410
		TD			5
1% Secant Modulus		MD	ASTM D-882	psi (MPa)	167,000 (1150)
		TD			246,000 (1700)
Elmendorf Tear Strength		MD	ASTM D-1922	g/mil	11
		TD			710
Dart Drop Impact, F ₅₀			ExxonMobil Method	g/mil	< 37

1. Film data was obtained on a 3 1/2" blown film line (pocket) with a 2:5:1 blow-up ratio and 60 thousands die gap
2. Values given are typical and should not be interpreted as specification.

FDA Status

HD-7845 is an olefin copolymer which complies with FDA Regulations 21 CFR 177.1520 (c) 3.1 and 3.2, and may be used in articles which are intended to contact foods at or below cooking temperatures.

AMERICAS Revised 11/99

©2000 ExxonMobil. The user may forward, distribute, and/or photocopy this copyrighted document only if unaltered and complete, including all of its headers, footers, disclaimers, and other information. You may not copy this document to a Web site. ExxonMobil does not guarantee the typical (or other) values. Analysis may be performed on representative samples and not the actual product shipped. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We based the information on data believed to be reliable on the date compiled, but we do not represent, warrant, or otherwise guarantee, expressly or impliedly, the merchantability, fitness for a particular purpose, suitability, accuracy, reliability, or completeness of this information or the products, materials, or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage, or injury directly or indirectly suffered or incurred as a result of or related to anyone using or relying on any of the information in this document. There is no warranty against patent infringement, nor any endorsement of any product or process, and we expressly disclaim any contrary implication. The terms, "we", "our", "ExxonMobil Chemical", or "ExxonMobil" are used for convenience, and may include any one or more of ExxonMobil Chemical Company, Exxon Mobil Corporation, or any affiliates they directly or indirectly steward. The ExxonMobil Chemical Emblem and the "Interlocking X" Device are trademarks of Exxon Mobil Corporation.



FINATHENE[®]

High Density
Polyethylene

7208

<u>Resin Properties⁽¹⁾</u>	<u>Typical Value</u>	<u>ASTM Method</u>
Melt Flow Index, g/10 min		D-1238
190°C/2.16 kg	0.42	
190°C/5 kg	1.6	
Density, g/cm ³	0.959	D-792
Melting Point, °F	265	D-3417
<u>Mechanical Properties⁽¹⁾⁽²⁾</u>		
Tensile Strength at Yield, psi	4,150	D-638, Type IV specimen, 2 in/min
Elongation at Break, %	>750	D-638, Type IV specimen, 2 in/min
Secant Modulus of Elasticity @ 2% strain, psi	160,000	D-638, Type IV specimen, 2 in/min
Flexural Modulus, psi	150,000	D-790

SPECIALTY HDPE EXTRUSION RESIN

Characteristics

- Medium molecular weight
- Narrow molecular weight distribution
- Designed for high speed orientation
- Excellent tensile strength

Applications

- Monofilament
- Slit tape
- Woven and knitted fabrics
- Specialty films

7208 4/02

RECEIVED
JUN 17 2003
TC 1700

- (1) Data developed under laboratory conditions and are not to be used as specification, maxima or minima.
- (2) The data listed was determined on compression molded specimens and may, therefore, deviate from molded and extruded specimens.



ATOFINA

15710 JFK Blvd.
Houston, TX 77032

P.O. Box 674411
Houston, TX 77267-4411

Phone: (281) 227-5249
Fax: (281) 227-5252

1-800-344-FINA

All tests were run under laboratory conditions. ASTM (where applicable) testing procedures. The data are intended as a general guide only and do not necessarily represent results that may be obtained elsewhere. The use of Finathene products must be guided by the users own methods for selection of proper formulation. ATOFINA PETROCHEMICALS, INC. disclaims any responsibility for misuse or miss application of its products. ATOFINA MAKES NO WARRANTY OF MERCHANTABILITY AND THERE IS NO WARRANTY THAT GOODS SUPPLIED SHALL BE FIT FOR ANY PARTICULAR PURPOSE. ATOFINA's liability and customer's exclusive remedy for any claims arising out of sales of its products are expressly limited at customer option to replacement of non-performing goods or payment not to exceed the purchase price plus transportation charges thereon in respect to any material which damage is claimed.